

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
Internation Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> :  
C03C 13/00, 13/06

A1

(11) International Publication Number: WO 97/30002

(43) International Publication Date: 21 August 1997 (21.08.97)

(21) International Application Number: PCT/FI97/00096

(22) International Filing Date: 14 February 1997 (14.02.97)

(30) Priority Data:  
960705 16 February 1996 (16.02.96) FI

(71) Applicant (for all designated States except US): PARTEK  
PAROC OY AB [FI/FI]; Sörnäisten rantatie 23, FIN-00500  
Helsinki (FI).

(72) Inventors; and

(75) Inventors/Applicants (for US only): PERANDER, Michael  
[FI/FI]; Väderkvamsvägen 10, FIN-21600 Pargas (FI).  
HAKALA, Jan [FI/FI]; Kardinalgatan 3 L 108, FIN-20380  
Åbo (FI).

(74) Agent: OY JALO ANT-WUORINEN AB; Iso Roobertinkatu  
4-6 A, FIN-00120 Helsinki (FI).

(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR,  
BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE,  
HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS,  
LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL,  
PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA,  
UG, US, UZ, VN, YU, ARIPO patent (KE, LS, MW, SD,  
SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU,  
TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI,  
FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent  
(BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD,  
TG).

Published

With international search report.

(54) Title: MINERAL FIBRE

(57) Abstract

The invention concerns an iron poor mineral fibre having a high temperature resistance. The mineral fibre has the following composition in % by weight: SiO<sub>2</sub> 35 - 45, Al<sub>2</sub>O<sub>3</sub> 18 - 25, TiO<sub>2</sub> 0 - 3, MgO 12 - 20, CaO 10 - 20, Na<sub>2</sub>O + K<sub>2</sub>O 0 - 3, iron (Fe<sub>2</sub>O<sub>3</sub>+FeO) 0 - 3, B<sub>2</sub>O<sub>3</sub> 0 - 3, P<sub>2</sub>O<sub>5</sub> 0 - 4, other 0 - 3, whereby the sum of FeO + MgO  $\geq$  15 % by weight.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

|    |                          |    |  |    |                          |
|----|--------------------------|----|--|----|--------------------------|
| AM | Armenia                  | GB | United Kingdom                           | MW | Malawi                   |
| AT | Austria                  | GE | Georgia                                  | MX | Mexico                   |
| AU | Australia                | GN | Guinea                                   | NE | Niger                    |
| BB | Barbados                 | GR | Greece                                   | NL | Netherlands              |
| BE | Belgium                  | HU | Hungary                                  | NO | Norway                   |
| BF | Burkina Faso             | IE | Ireland                                  | NZ | New Zealand              |
| BG | Bulgaria                 | IT | Italy                                    | PL | Poland                   |
| BJ | Benin                    | JP | Japan                                    | PT | Portugal                 |
| BR | Brazil                   | KE | Kenya                                    | RO | Romania                  |
| BY | Belarus                  | KG | Kyrgyzstan                               | RU | Russian Federation       |
| CA | Canada                   | KP | Democratic People's Republic<br>of Korea | SD | Sudan                    |
| CF | Central African Republic | KR | Republic of Korea                        | SE | Sweden                   |
| CG | Congo                    | KZ | Kazakhstan                               | SG | Singapore                |
| CH | Switzerland              | LI | Liechtenstein                            | SI | Slovenia                 |
| CI | Côte d'Ivoire            | LK | Sri Lanka                                | SK | Slovakia                 |
| CM | Cameroon                 | LR | Liberia                                  | SN | Senegal                  |
| CN | China                    | LT | Lithuania                                | SZ | Swaziland                |
| CS | Czechoslovakia           | LU | Luxembourg                               | TD | Chad                     |
| CZ | Czech Republic           | LV | Latvia                                   | TG | Togo                     |
| DE | Germany                  | MC | Monaco                                   | TJ | Tajikistan               |
| DK | Denmark                  | MD | Republic of Moldova                      | TT | Trinidad and Tobago      |
| EE | Estonia                  | MG | Madagascar                               | UA | Ukraine                  |
| ES | Spain                    | ML | Mali                                     | UG | Uganda                   |
| FI | Finland                  | MN | Mongolia                                 | US | United States of America |
| FR | France                   | MR | Mauritania                               | UZ | Uzbekistan               |
| GA | Gabon                    |    |  | VN | Viet Nam                 |

## Mineral fibre

The present invention relates to a fiberizable mineral composition as well as mineral fibres made therefrom which have a high temperature resistance.

Mineral fibres made by melting and centrifuging of a mineral raw material, such as rock, slag or similar, are used to a high degree for the manufacture of mineral fibre mats and blankets, primarily for heat and sound insulation purposes in the construction industry. In addition to the manufactured mat exhibiting a good insulating capacity against heat and sound, one has recently started to pay more attention to the properties of the mat also from a labour hygienic point of view.

A wide selection of insulating products are available on the market which exhibit not only different heat insulating properties, but also a varying degree of temperature resistance. Temperature resistant mineral fibre products are intended to mean products which can resist elevated temperatures under prolonged periods of time without changing shape or dimensions to any higher degree. Such products are thus attractive from a fire prevention point of view.

Conventional glass fibre is temperature resistant at temperatures up to appr. 550°C, whereas the temperature resistance of conventional rock wool is better, up to appr. 700°C. There is, however, an interest in products having an even higher temperature resistance, up to 1100-1200°C, and such products are also available on the market.

Such temperature resistant fibre products contain as the main oxides silicium oxide  $\text{SiO}_2$ , and aluminium oxide,  $\text{Al}_2\text{O}_3$ , and in addition often an earth alkaline metal oxide, such as calcium oxide,  $\text{CaO}$ , or magnesium oxide,  $\text{MgO}$ . In addition, such products can contain varying amounts of other oxides, such as titanium oxide,  $\text{TiO}_2$ , manganese oxide,  $\text{MnO}$ , boron oxide,  $\text{B}_2\text{O}_3$ , zirconium oxide,  $\text{ZrO}_2$ , chromium oxide,  $\text{Cr}_2\text{O}_3$ , the alkali oxides sodium and potassium oxide,  $\text{Na}_2\text{O}$  and  $\text{K}_2\text{O}$ , as well as contaminants. As examples of known art relevant in this connection, reference is made, for example, to US 4,461,840 and DE OS 1 496 662.

According to the last mentioned publication, an especially advantageous composition is obtained when the raw material melt contains appr. 4 - 12 % of iron oxides. In the mineral melt, the iron oxides are primarily present as divalent iron (appr. 75-90%) and to a lesser degree in the form of trivalent iron (appr. 25-10%). The iron content of the mineral melt is a consequence of the fact that many economically attractive raw materials contain iron to higher or lower degree. The presence of divalent iron has an advantageous effect on the temperature resistance of the fibre, its presence for this reason being beneficial. However, in recent times, one has seriously started to pay attention to the possible toxic effects of iron in mineral fibres, especially in fibres which in addition to temperature resistance have an increased solubility in biological fluids.

Due to the toxicity risk, there is thus a need to minimize the total content of iron in mineral fibres. This, however, leads to an impairment of the temperature resistance.

According to the present invention the problem relating to decreased temperature resistance when using small amounts of iron has been solved in a mineral fibre composition, which contains as the main oxides silicium dioxide, aluminium oxide and calcium oxide. The problem has been solved by compensating the absence or the low level of divalent iron by including in such a composition magnesium oxide in an amount so that the total amount of magnesium oxide MgO and iron oxide FeO is at least 15 % by weight. In this way a mineral fibre composition is obtained which is both temperature resistant and has low toxicity.

More specifically, the invention refers to a mineral fibre which has the following composition in % by weight

|    |  |      |    |
|----|--|------|----|
|    |  |      | 3  |
|    | SiO <sub>2</sub>                           | 35 - | 45 |
|    | Al <sub>2</sub> O <sub>3</sub>             | 18 - | 25 |
|    | TiO <sub>2</sub>                           | 0 -  | 3  |
|    | MgO  | 12 - | 20 |
| 5  | CaO  | 10 - | 20 |
|    | Na <sub>2</sub> O + K <sub>2</sub> O       | 0 -  | 3  |
|    | iron (Fe <sub>2</sub> O <sub>3</sub> +FeO) | 0 -  | 3  |
|    | B <sub>2</sub> O <sub>3</sub>              | 0 -  | 3  |
|    | P <sub>2</sub> O <sub>5</sub>              | 0 -  | 4  |
| 10 | other                                      | 0 -  | 3  |

whereby the sum of FeO+ MgO  $\geq$  15 % by weight.

15 The denomination "other" components above encompasses such possible contaminants which are not of substantial importance for the properties of the manufactured fibre.

20 It is known that within the range 0 - appr. 15 % the aluminium oxide content is direct proportional to the stability of the fibre in biological solutions, that is the more aluminium oxide the composition contains, the more stable or poorly soluble is the product. However, at a higher level, the tendency becomes reversed so that the solubility of the fibre increases in relation to the aluminium oxide content. According to the invention, a fibre has thus been made having a good heat resistance but a low toxicity and a high solubility in biological solutions.

25 Preferably the composition contains essentially equal amounts of MgO and CaO. According to a further preferred embodiment, the sum FeO + MgO + CaO  $\leq$  32 % by weight.

30 According to a preferred embodiment, the invention concerns a fibre having the following composition in % by weight

|    |  |      |    |
|----|--|------|----|
|    |  |      | 4  |
|    | SiO <sub>2</sub>                           | 38 - | 42 |
|    | Al <sub>2</sub> O <sub>3</sub>             | 18 - | 22 |
|    | TiO <sub>2</sub>                           | 1 -  | 3  |
|    | MgO  | 14 - | 18 |
| 5  | CaO  | 14 - | 18 |
|    | Na <sub>2</sub> O + K <sub>2</sub> O       | 0 -  | 2  |
|    | iron (Fe <sub>2</sub> O <sub>3</sub> +FeO) | 1 -  | 3  |
|    | B <sub>2</sub> O <sub>3</sub>              | 1 -  | 2  |
|    | P <sub>2</sub> O <sub>5</sub>              | 1 -  | 2  |
| 10 | other                                      | 0 -  | 2  |

whereby  $\text{FeO} + \text{MgO} \geq 15\%$  by weight.

15 According to a very special embodiment, the invention refers to a fibre containing substantially

|    |  |    |
|----|--|----|
|    | SiO <sub>2</sub>                           | 38 |
|    | Al <sub>2</sub> O <sub>3</sub>             | 20 |
|    | TiO <sub>2</sub>                           | 2  |
| 20 | MgO  | 15 |
|    | CaO  | 15 |
|    | Na <sub>2</sub> O + K <sub>2</sub> O       | 1  |
|    | iron (Fe <sub>2</sub> O <sub>3</sub> +FeO) | 3  |
|    | B <sub>2</sub> O <sub>3</sub>              | 2  |
| 25 | P <sub>2</sub> O <sub>5</sub>              | 2  |
|    | other                                      | 2. |

30 The mineral composition is made in a conventional manner by mixing suitable raw material a such as stone, sand, dolomite, apatite, olivine, glass, or various slags and other suitable waste materials in suitable proportions. According to a preferred embodiment, the predominant raw material is slag fom iron manufactu-  
re, as such a product in itself is already iron poor. The desired increased alu-

minium oxide content can be obtained by adding suitable aluminium containing raw materials, for example bauxite, in suitable amounts. Mineral fibres are manufactured from the composition in a conventional manner, for example using cascade centrifugation.

5

The following example illustrates the invention without restricting the same.

10

15

20

25

30

**Example**

## Example

In a cupola furnace the following components are charged having the compositions indicated in the table, in the amounts indicated in % by weight.

|                                | Calc.<br>bauxite | Quartz<br>sand | Slag | Apatite | Olivine<br>sand |
|--------------------------------|------------------|----------------|------|---------|-----------------|
| amount:<br>compo-<br>nent:     | 20.0             | 14.0           | 33.0 | 5.0     | 28.0            |
| SiO <sub>2</sub>               | 5.0              | 99.1           | 36.0 | 3.2     | 42.0            |
| Al <sub>2</sub> O <sub>3</sub> | 86.5             | 0.6            | 9.0  | 0.3     | 0.5             |
| TiO <sub>2</sub>               | 4.0              | 0.0            | 1.0  | 0.0     | 0.0             |
| MgO                            | 0.0              | 0.0            | 10.2 | 0.5     | 49.3            |
| CaO                            | 0.0              | 0.0            | 37.8 | 50.8    | 0.0             |
| Na <sub>2</sub> O+             |                  |                |      |         |                 |
| K <sub>2</sub> O               | 0.3              | 0.1            | 1.1  | 0.0     | 0.0             |
| iron                           | 1.9              | 0.1            | 0.3  | 0.8     | 7.1             |
| B <sub>2</sub> O <sub>3</sub>  | 0.0              | 0.0            | 0.0  | 0.0     | 0.0             |
| P <sub>2</sub> O <sub>5</sub>  | 0.2              | 0.0            | 0.0  | 33.0    | 0.0             |
| other                          | 0.0              | 0.1            | 1.1  | 8.3     | 1.1             |

From the melt obtained fibres are made in a conventional manner by cascade centrifugation, which fibres are collected onto a conveyor to form a mineral fibre mat. The mineral fibres have the following composition.



|    |   |      |
|----|---|------|
|    | SiO <sub>2</sub>                            | 40.0 |
|    | Al <sub>2</sub> O <sub>3</sub>              | 21.2 |
|    | TiO <sub>2</sub>                            | 1.2  |
|    | MgO   | 17.8 |
| 5  | CaO   | 15.5 |
|    | Na <sub>2</sub> O + K <sub>2</sub> O        | 0.4  |
|    | iron (Fe <sub>2</sub> O <sub>3</sub> + FeO) | 1.7  |
|    | B <sub>2</sub> O <sub>3</sub>               | 0    |
|    | P <sub>2</sub> O <sub>5</sub>               | 1.7  |
| 10 | other                                       | 0.5. |

## Claims

1. Mineral fibre, characterized in that it has the following composition in % by weight:

|    |  |    |   |    |
|----|--|----|---|----|
|    | SiO <sub>2</sub>                           | 35 | - | 45 |
|    | Al <sub>2</sub> O <sub>3</sub>             | 18 | - | 25 |
|    | TiO <sub>2</sub>                           | 0  | - | 3  |
| 10 | MgO  | 12 | - | 20 |
|    | CaO  | 10 | - | 20 |
|    | Na <sub>2</sub> O + K <sub>2</sub> O       | 0  | - | 3  |
|    | iron (Fe <sub>2</sub> O <sub>3</sub> +FeO) | 0  | - | 3  |
|    | B <sub>2</sub> O <sub>3</sub>              | 0  | - | 3  |
| 15 | P <sub>2</sub> O <sub>5</sub>              | 0  | - | 4  |
|    | other                                      | 0  | - | 3  |

whereby the sum FeO+ MgO  $\geq$  15 % by weight.

2. The mineral fibre according to claim 1, characterized in that it contains substantially equal amounts of MgO and CaO.

3. The mineral fibre according to claim 1 or 2, characterized in that the FeO + MgO + CaO  $\leq$  32 % by weight.

4. The mineral fibre according to claim 1, 2 or 3, characterized in that it has the following composition in % by weight:

|    |                                |    |   |    |
|----|--------------------------------|----|---|----|
|    | SiO <sub>2</sub>               | 38 | - | 42 |
| 30 | Al <sub>2</sub> O <sub>3</sub> | 18 | - | 22 |
|    | TiO <sub>2</sub>               | 1  | - | 3  |
|    | MgO                            | 14 | - | 18 |

|   |  |      |    |
|---|--|------|----|
|   |  |      | 9  |
|   | CaO  | 14 - | 18 |
|   | Na <sub>2</sub> O + K <sub>2</sub> O       | 0 -  | 2  |
|   | iron (Fe <sub>2</sub> O <sub>3</sub> +FeO) | 1 -  | 3  |
|   | B <sub>2</sub> O <sub>3</sub>              | 1 -  | 2  |
| 5 | P <sub>2</sub> O <sub>5</sub>              | 1 -  | 2  |
|   | other                                      | 0 -  | 2  |

whereby  $\text{FeO} + \text{MgO} \geq 15$  % by weight.

- 10 5. The mineral fibre according to claim 4, characterized in that it has substantially the following composition in % by weight:

|    |  |    |
|----|--|----|
|    | SiO <sub>2</sub>                           | 38 |
|    | Al <sub>2</sub> O <sub>3</sub>             | 20 |
| 15 | TiO <sub>2</sub>                           | 2  |
|    | MgO  | 15 |
|    | CaO  | 15 |
|    | Na <sub>2</sub> O + K <sub>2</sub> O       | 1  |
|    | iron (Fe <sub>2</sub> O <sub>3</sub> +FeO) | 3  |
| 20 | B <sub>2</sub> O <sub>3</sub>              | 2  |
|    | P <sub>2</sub> O <sub>5</sub>              | 2  |
|    | other                                      | 2. |

# 1

## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/FI 97/00096

### A. CLASSIFICATION OF SUBJECT MATTER

IPC6: C03C 13/00, C03C 13/06  
According to International Patent Classification (IPC) or to both national classification and IPC

### B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

### C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category* | Citation of document, with indication, where appropriate, of the relevant passages                            | Relevant to claim No. |
|-----------|---|-----------------------|
| A         | WO 8705007 A1 (MANVILLE CORPORATION),<br>27 August 1987 (27.08.87), page 10,<br>line 1 - line 16<br><br>----- | 1-5                   |

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

- |   |   |
|---|---|
| <p>* Special categories of cited documents</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> | <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&amp;" document member of the same patent family</p> |
|---|---|

Date of the actual completion of the international search

15 May 1997

Date of mailing of the international search report

03-06-1997

Name and mailing address of the ISA/  
Swedish Patent Office  
Box 5055, S-102 42 STOCKHOLM  
Facsimile No. +46 8 666 02 86

Authorized officer

May Hallne  
Telephone No. +46 8 782 25 00

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/FI 97/00096

| Patent document<br>cited in search report | Publication<br>date | Patent family<br>member(s) | Publication<br>date |
|---|---------------------|----------------------------|---------------------|
| WO 8705007 A1                             | 27/08/87            | AU 590393 B                | 02/11/89            |
|   |                     | AU 6948887 A               | 09/09/87            |
|   |                     | CA 1271785 A               | 17/07/90            |
|   |                     | EP 0257092 A               | 02/03/88            |
|   |                     | FI 94520 B                 | 15/06/95            |
|   |                     | JP 7042139 B               | 10/05/95            |
|   |                     | JP 63502746 T              | 13/10/88            |
|   |                     | NO 178886 B                | 18/03/96            |
|   |                     | US 5332699 A               | 26/07/94            |

---